



*Making the World Friction Free*



## PBG-L Tyre Lubricant Technical Data Sheet

ASTM D-445	Base oil viscosity in centistokes	40 °C	998
		100 °C	56
ASTM D-97	Pour point		-26 °C
ASTM D-2270	Viscosity index		102
ASTM D-217	Cone Penetration	UNWORKED	403
		WORKED	398
N.L.G.I. GRADE	Consistency		00
ASTM D-2265	Drop Point		Not determined
ASTM D-2596	Extreme Pressure Properties (Four Ball Method)	Load Wear Index	66.50
		Weld Load	500Kg

Typical properties, whereas stated, are to be considered as representative of current production and should not be treated as specifications. While all the information presented in this document is believed to be reliable and to represent the best available data on the products, NO GUARANTEE, WARRANTY, OR REPRESENTATIONS IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. Products may be toxic and require special precautions in handling. For all products listed, user should obtain detailed information on toxicity, together with proper shipping, handling, and storage procedures, and comply with all applicable safety and environmental standards



Quechem, Div of Gra flo Inc.  
P.O.BOX 64  
Green Valley, Ontario,  
Canada, K0C 1L0

Telf: 1-613-525-5858  
Fax: 1-613-525-5883  
Email: sales@quechem.com  
Website: www.quechem.com